

## Description

Lexan\* 9030FA sheet is a transparent sheet with polished surface and is formulated and manufactured to comply with European food contact Directive 2002/72/EC, as amended. This grade does not contain hazardous substances regulated by RoHS Directive 2002/95/EC and has no surface treatment for either UV protected or mar-resistance. Lexan 9030FA sheet combines high impact and temperature resistance with optical clarity and can be excellent candidate for chocolate molds and food packaging. Lexan 9030FA sheet can be cut, sawn, drill, milling and bent easily using standard workshop equipment without the risk of cracking and breakage. Lexan 9030FA sheet can be easily thermoformed into complex parts like dishwasher cleanable chocolate molds and will retain its properties.

## Typical Property Values ♦

Property	Value	Unit	Test Method
<b>Physical</b>			
Density	1.2	g/cm <sup>3</sup>	ISO 1183
Water absorption, 24 hours	10	mg.	ISO 62
Water absorption, saturation /23°C	0.35	%	ISO 62
Mould shrinkage	0.6-0.8	%	ASTM-D955
Poison's ratio	0.38	-	ASTM-D638
<b>Mechanical</b>			
Tensile stress at yield 50 mm/min	60	MPa	ISO 527
Tensile stress at break 50 mm/min	70	MPa	ISO 527
Tensile strain at yield 50 mm/min	6	%	ISO 527
Tensile strain at break 50 mm/min	120	%	ISO 527
Tensile modulus 1 mm/min	2350	MPa	ISO 527
Flexural stress at yield 2 mm/min	90	MPa	ISO 178
Flexural modulus 2 mm/min	2300	MPa	ISO 178
Hardness H358/30	95	MPa	ISO 2039/1
<b>Impact</b>			
Charpy impact, notched	35	kJ/m <sup>2</sup>	ISO 179/2C
Izod impact, unnotched 23°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod impact, unnotched -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod impact, notched 23°C	65	kJ/m <sup>2</sup>	ISO 180/1A
Izod impact, notched -30°C	10	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Vicat B/120	145	°C	ISO 306
HDT/Ae, 1.8 MPa edgew. 120*1*04/s=100	127	°C	ISO 75
Thermal conductivity	0.2	W/m.°C	DIN52612
Coef. of Lin. Therm. Exp. extr. 23-80°C	7.00E-05	1/°C	DIN53752
Ball pressure test 125 ±2°C	Passes	-	IEC335-1
Thermal Index. Electrical Properties	100	°C	UL746B
Thermal Index. Mech. prop. with impact	100	°C	UL746B
Thermal Index. Mech. prop. w/o impact	100	°C	UL746B
<b>Flammability</b>			
Oxygen Index †)	25	%	ISO 4589
Glow Wire Test, 850°C, passes at	1	mm	IEC695-2-1
Glow Wire Test, 960°C, passes at	3.2	mm	IEC695-2-1
<b>Optical</b>			
Light transmission <sup>‡)</sup> 3 mm	89	%	ASTM-D1003

♦ These property values have been derived from Lexan\* resin data for the material used to produce this sheet product. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.

†) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

‡) Light transmission value may vary by + or - 5%.

\* Trademarks of SABIC Innovative Plastics IP BV

## Chemical Resistance

Taking into account the complexity of chemical compatibility, all chemicals which come into contact with Lexan 9030FA sheet should be tested. Consult our technical service center for more technical info.

## Product Availability

<b>Product code:</b>	Lexan 9030FA
<b>Standard gauge : #</b>	1, 1.5, 2, 2.5, 3 mm
<b>Standard width:#</b>	1250 mm
<b>Standard length: #</b>	2050 mm
<b>Standard color: #</b>	11204
<b>Masking, top: #</b>	PE coex translucent white 50 mu
<b>Masking, bottom</b>	PE coex translucent white 50 mu

# Other gauges and other dimensions upon request and are subject to minimum order quantities.



\* Trademark of SABIC Innovative Plastics IP BV

Americas:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
Tel. (1) (413) 448 5400  
Fax. (1) (413) 448 7506  
Toll free: 1-800 451 3147

Europe:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
Plasticslaan 1  
NL - 4612 PX Bergen op Zoom  
The Netherlands  
Tel. (31) (164) 292911  
Fax. (31) (164) 293272

Pacific:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
1266 Nanjin Road (W)  
Plaza 66, 17th Floor  
200040 Shanghai, China  
Tel. (86) 21 62881088  
Fax. (86) 21 62880818

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

\* Trademark of SABIC Innovative Plastics IP BV

[www.sabic-ip.com](http://www.sabic-ip.com)

Latest update SABIC (01/2008)